



AWS C3.7M/C3.7:2005 Official Interpretation

Subject: Temperature Uniformity Requirements

Document: AWS C3.7M/C3.7:2005, *Specification for Aluminum Brazing*

Specification Provision: Page 4, Subclause 5.3.2 (Temperature Uniformity Requirements)

Inquiry: Do salt baths for brazing aluminum having a solidus of less than 1120°F have to meet a $\pm 5^\circ\text{F}$, SAE/AMS 2750, *Pyrometry*, Class 1 temperature uniformity requirement?

Response Yes