



AWS D1.1 Interpretation

Subject: Welder Qualification – Pipe Diameters Qualified

Code Edition: D1.1:2002

Code Provision: Table 4.9 and Table 4.10

AWS Log: D1.1-02-I06 (INQ-29)

Inquiry: For a welder who is qualified by a plate groove test, what diameter of pipe is the welder qualified to weld fillet welds and PJP welds?

Response: A welder qualified by a plate groove test is also qualified to weld fillet welds on all diameters of pipe and PJP welds over 24” diameter within the position and thickness limitations of Table 4.9 and 4.10.

AWS D1.1, Structural Welding Code—Steel, is prepared by the AWS Structural Welding Committee. Because the Code is written in the form of a specification, it cannot present background material or discuss the committee’s intent.

Since the publication of the first edition of the Code, the nature of inquiries directed to the American Welding Society and the Structural Welding Committee has indicated that there are some requirements in the Code that are either difficult to understand or not sufficiently specific, and other that appear to be overly conservative.

It should be recognized that the fundamental premise of the Code is to provide general stipulations applicable to any situation and to leave sufficient latitude for the exercise of engineering judgment. Another point to be recognized is that the Code represents the collective experience of the committee; and, while some provisions may seem overly conservative, they have been based on sound engineering practice.