



## AWS D1.5 Interpretation

**Subject:** Ultrasonic (UT) Procedures – Screen  
**Code Edition:** D1.5:2002  
**Code Provision:** Table 6.2  
**AWS Log:** D1.5-02-I05

**Inquiry:** Is it the intent of the code that a 45mm [1.75 inches] weld tested with the 10 inch screen distance will be acceptable in this instance, or should a 15 inch screen distance or another angle of transducer be used, and if so what angle of transducer.

**Response:** Yes, it is the intent to use a 10” scale. However, 6.18.5.1 also permits a 15” scale, as required.

---

AASHTO/AWS D1.5, Bridge Welding Code, is prepared by the AWS Structural Welding Committee. Because the Code is written in the form of a specification, it cannot present background material or discuss the committee’s intent.

Since the publication of the first edition of the Code, the nature of inquiries directed to the American Welding Society and the Structural Welding Committee has indicated that there are some requirements in the Code that are either difficult to understand or not sufficiently specific, and other that appear to be overly conservative.

It should be recognized that the fundamental premise of the Code is to provide general stipulations applicable to any situation and to leave sufficient latitude for the exercise of engineering judgment. Another point to be recognized is that the Code represents the collective experience of the committee; and, while some provisions may seem overly conservative, they have been based on sound engineering practice.